

**Product Data Sheet**  
Edition 18/09/2006  
Identification no:  
02 03 02 04 005 0 000009  
SikaTop®-122

# SikaTop®-122

## Cementitious Concrete Repair Mortar

### Product Description

SikaTop® -122 is a two component polymer modified cement based fibre reinforced concrete waterproof repair mortar.

### Uses

- For repairing all types of concrete
- For high strength repairs
- Repairs to floors
- Horizontal and vertical repairs
- Hand applied repairs
- For exterior and interior use

### Characteristics / Advantages

- Pre-batched for quality
- Fast and easy to apply
- No water required
- Free of chloride ions
- Suitable for drinking water contact

### Tests

**Approval / Standards**      Approved for potable water contact.

### Product Data

#### Form

**Appearance /Colours**      Cement grey (Component A: white liquid, Component B: grey powder)

**Packaging**                      25kg and 10kg bags

#### Storage

**Storage Conditions/ Shelf-Life**      9 months from date of production if stored properly in original unopened, sealed and undamaged packaging in dry and cool conditions.

### Technical Data

**Chemical Base**                      Portland cement, polymer redispersable liquid, selected aggregates and additives and microfibres.

**Density**                              Fresh mortar density: ~ 2.1 kg/l

**Grading**                              D<sub>max</sub>: 1.5 mm

**Layer Thickness**                      4.0 mm min. / 20 mm max. (vertical) / 75 mm max. (horizontal if bulked out)



---

## Mechanical / Physical Properties

---

<b>Compressive Strength</b>	28 days > 55 N/mm <sup>2</sup>
<b>Flexural Tensile Strength</b>	28 days ~ 10-12 N/mm <sup>2</sup>
<b>Bond Strength</b>	~ 1.0-3.0 N/mm <sup>2</sup> (substrate failure with Bonding Primer)
<b>E-Modulus</b>	19.3 kN/mm <sup>2</sup>

---

## System Information

---

<b>System Structure</b>	SikaTop 122 is part of the SikaTop Concrete Repair System. SikaTop <sup>®</sup> Armatec-110 EpoCem: Reinforcement coating SikaTop <sup>®</sup> -121: Bonding primer SikaTop <sup>®</sup> -122: Hand applied repair mortar SikaTop <sup>®</sup> -122HB: High build hand applied repair mortar SikaTop <sup>®</sup> -121: Smoothing coat Sika <sup>®</sup> FerroGard <sup>®</sup> - 903: Corrosion inhibitor
-------------------------	--

---

## Application Details

---

<b>Consumption</b>	This depends on the substrate roughness and thickness of layer applied. As a guide, ~ 2.1 kg/m <sup>2</sup> /mm.
--------------------	---

---

<b>Substrate Quality</b>	<p><i>Concrete</i></p> <p>The concrete shall be free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials.</p> <p><i>Steel reinforcement</i></p> <p>Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed to a minimum standard of SA2½.</p> <p>Reference should also be made to BS EN1504-10:2003 for specific requirements.</p>
	<p><b>Substrate Preparation / Bonding Primer/ Reinforcement Coating</b></p> <p><i>Concrete:</i></p> <p>Delaminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable mechanical or very high pressure waterblasting [up to 110 mPa (16500 psi)] techniques.</p> <p>Tying wire fragments, nails and other metal debris embedded in the concrete should be removed where possible.</p> <p>The edges where concrete is removed should be cut at a minimum angle of 90° to avoid undercutting and a maximum angle of 135° to reduce the possibility of debonding with the top surface of the adjacent sound concrete and should be roughened sufficiently to provide a mechanical key between the original material and SikaTop®-122.</p> <p>Ensure sufficient concrete is removed from around reinforcement to allow coating and compaction of the repair material.</p> <p><i>Steel reinforcement:</i></p> <p>Surfaces should be prepared using abrasive blast cleaning techniques or high pressure waterblasting [up to 60 mPa (9000 psi)] techniques.</p> <p>Where exposed reinforcement is contaminated with chloride or other material which may cause corrosion, the reinforcement shall be cleaned by low pressure waterblasting [up to 18 mPa (2700 psi)].</p> <p><i>Bonding primer:</i></p> <p>On a well prepared and roughened substrate a bonding primer is generally not required.</p> <p>When a bonding primer is not required pre-wet the surface. The surface should not be allowed to dry before application of the concrete repair mortar. The surface should achieve a dark matt appearance without glistening and surface pores and pits should not contain water.</p> <p>When a bonding primer is necessary apply SikaTop®-121 or SikaTop® Armatec-110 EpoCem® (Refer to the relevant Product Data Sheets).</p> <p>Site adhesion values - Structural Repair 1.2-1.5 mPa Non Structural repairs minimum value 0.7 mPa</p> <p><i>Reinforcement coating:</i></p> <p>Where a reinforcement coating is required as a barrier, apply to the whole exposed circumference two coats of SikaTop® Armatec-110 EpoCem®. (Refer to the relevant Product Data Sheet).</p> <p>Reference should also be made to BS EN1504-10:2003 for specific requirements.</p>

**Application Conditions / Limitations**

<b>Substrate Temperature</b>	+8°C min. / +30°C max.
<b>Air Temperature</b>	+8°C min. / +30°C max.

---

**Application Instructions**

---

**Mixing** Mix together both Components A (liquid) and B (powder).

---

**Mixing Time** Shake component A before using. Pour approximately ½ component A into mixing container and add component B slowly while mixing. When homogeneous, add the remainder of the component A and remix. Normal mixing time depends on the type of mixer used, 2-3 minutes is average. Mix so as to entrain as little air as possible and use without delay.

When mixed, the produce may be bulked out with dry, dust free aggregate (40% by wt of 3-6 mm granite chippings) and remixed to a uniform consistency.

---

**Application Method / Tools**

*Hand Applied*

If a bonding primer has been used apply repair mortar “wet on wet”.

The repair mortar shall be worked into the prepared pre-wetted substrate between the minimum and maximum layer thicknesses and shall be compacted without inclusion of entrapped air pockets using a trowel or gloved hand.

Where layers are to be built up to prevent sagging or slumping, each layer should be allowed to stiffen before applying subsequent layers “wet on wet”. When layers cannot be applied “wet on wet”, or if more than 6 hours between layers apply a bonding primer of SikaTop®-121 or SikaTop® Armatec-110 EpoCem® and apply repair mortar “wet on wet”.

Reference shall be made to BS EN1504-10:2003 for specific requirements.

---

**Cleaning of Tools**

Clean all tools and application equipment with water immediately after use. Hardened/cured material can only be mechanically removed.

---

**Potlife**

~ 30 minutes (at +20°C)

---

**Notes on Application / Limitations**

Avoid application in direct sun and/or strong wind and/or rain.

Do not add water.

Apply only to sound, prepared substrates.

Do not add water during the surface finishing as this will cause discoloration and cracking.

Protect freshly applied material from freezing.

---

**Curing Details**

**Curing Treatment**

It is essential to cure the repair mortar immediately after application for a minimum of 3-5 days to ensure full cement hydration and to minimise cracking. Use polythene sheeting taped down at the edges or other approved method.

Curing compounds shall not be used when they adversely affect subsequently applied products and systems.

Reference shall also be made to BS EN1504-10:2003 for specific requirements.

---

**Value Base**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

---

**Local Restrictions**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

---

**Health and Safety Information**

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

---

## Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Limited  
Watchmead  
Welwyn Garden City  
Hertfordshire  
AL7 1BQ  
United Kingdom

Phone +44 1707 394444  
Telefax +44 1707 329129  
[www.sika.co.uk](http://www.sika.co.uk), email: [sales@uk.sika.com](mailto:sales@uk.sika.com)

